



P.O. Box 1128 • Marietta OH 45750  
Phone: 740-374-3742 • Phone: 800-937-3746 • Fax: 740-374-6059

## Typical Properties

### ARC66G13

**Description:** Nylon 6/6, 13% Glass Filled, Lubricated

<u>Property</u>	<u>English Value</u>	<u>Test Reference</u>
Melt Point	494°F 257°C	ASTM D-789
Density	76.0 lb/ft <sup>3</sup> 1.22 gm/cm <sup>3</sup>	ASTM D-792
Tensile Strength	10.0 x 10 <sup>3</sup> psi 69 MPa	ASTM D-638
Elongation	4%	ASTM D-638
Flexural Modulus	6.5 x 10 <sup>5</sup> psi 4480 MPa	ASTM D-790
Flexural Strength	23.0 x 10 <sup>3</sup> psi 158 MPa	ASTM D-790
Notched Izod	.9 ft-lb/in. 48.9 J/m	ASTM D-256
Shrinkage	.004-.008 in/in	
Deflection Temp. @ 264 psi	460°F 238°C	ASTM D-648
Deflection Temp. @ 66 psi	485°F 252°C	ASTM D-648

*Properties indicated above are for natural color resins, dry as molded. Addition of colorants or additives may alter or degrade these properties.*

The test results are believed to be based on reliable procedures. Due to variable conditions or methods of processing. NO GUARANTEES OR WARRANTIES ARE EXPRESSED OR IMPLIED, INCLUDING THE IMPLIED WARRANTY OF MERCHANTABILITY FOR PARTICULAR PURPOSE. The above information is not to be construed as a license or a recommendation to infringe on any patents.